



**SERVICE TEMPERATURE**

Dry Service	450°F (232°C)
Spill/Splash	360°F (182°C)
Immersion Service*	300°F (149°C)

\* Immersion with solvents, mineral acids, or alkalines, or if over 150°F contact factory

**PUMP SPECIFICATIONS**

Pump Ratio	56:1 or greater
Minimum Output	5600 psi
Product Hose: Min. - Optimum I.D.	0.375 - 0.5 inch
Max. Length	50 feet

**MULTIPLE COATS:**

Second and subsequent coats must be applied before the previous coat has completely cross-linked. Apply additional coats when the previous coat will still string out (pigtail) and hold its shape when touched. If any slight tack remains, allow the product to cure, then brush blast before applying the next coat.

The same requirement applies when overlapping the seams of adjacent coating sections to create a continuous protective film. If the coating surface to be overlapped at the seam cannot be brush blasted, use a non-impact means such as power brushing or sanding to create a mechanical profile.

**CURE TIME (AT 75°F)**

Re-coat Window	1-1½ hours
Light Loading	12 hours
Immersion (Aqueous) Service	30 hours
Full or Chemical Service	7 days

**ORDERING INFORMATION**

For additional information, prices, or to place an order, please contact your ErgonArmor sales representative. If you do not know the name of your sales representative, call 877-98ARMOR.

Data Sheet Revised July 2009

All statements, technical information, and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties, express or implied. Sellers and manufacturers only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for the intended use, and user assumes all risk and liability whatsoever therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacturer.