SELECTION & SPECIFICATION DATA

Type Fast Drying Asphalt Cutback

Description Blackhawk 5159 Asphalt Cutback coating is

used for many metal corrosion and weather protection. Its high solids content gives it excellent coverage on marginally prepared metal and pavement surfaces, and it can also function as a primer for additional bituminous coatings.

Uses • Pavement coating

· Corrosion protection coating on steel substrates

· Primer for metal substrates

Color Black

Primer Self-priming

Topcoats Consult ErgonArmor

Finish Gloss

Dry Film 3 – 5 mils

Thickness (DFT)

Solids Content 59% ± 2% by weight

VOC Value(s) <450g/L (3.75 lbs/gal)

SUBSTRATES & SURFACE PREPARATION

All surfaces must be clean and free from debris

and loose scale material or anything that may interfere with adhesion or act as a bond breaker

with the desired substrate.

SAFETY

Safety Mixes and applications of this product present a

number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data

sheets before using.

Ventilation Thorough air circulation must be used during

and after application until the product is cured. User should test and monitor exposure levels to ensure all personnel are within safe limits. Consult

product SDS for further information.

MIXING & THINNING

Mixing No mixing required. Ready to use as is.

Thinning Do not thin.

Cleanup Mineral spirits

APPLICATION GUIDANCE

Airless Spray Pump size: 15:1 or greater
Single Leg or Pot Hose length: 20 ft x 1/2-inch ID

Brush Apply with a wide fiber brush in order to create a

smooth uniform film.

Roller Use a low nap phenolic core roller.

PACKAGING, ESTIMATING & HANDLING

 ITEM #
 PACKAGING

 K-5159-000-001
 Bulk - gallon

 K-5159-053-001-UN
 Drum - 53 gallons

 K-5159-275-001
 Tote - 270 gallons

Theoretical 220 square feet per gallon at 4 mils DFT

Coverage Rate

Storage & Estimated shelf life is 12 months when stored in a dry area at 75°F (24°C). Actual shelf life may

vary with storage conditions. Do not store below 40°F (4°C) or above 110°F (43°C). Store indoors. This product is not affected by excursions below these published storage temperatures, down to 10°F (-12°C), for a duration of no more than 14 days.

Always inspect the product prior to use.

TYPICAL PHYSICAL PROPERTIES

Viscosity, at 77°F (25°C)	75 cps
Specific gravity, at 60°F (16°C)	26.2
Density, at 60°F (16°C)	7.472 lbs/gal

Rev 12/21

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.