

## **SELECTION & SPECIFICATION DATA**

<b>Type</b>	Polymer Modified Asphalt Emulsion
<b>Description</b>	A blend of polymer and emulsified asphalts that provides a tough, monolithic, rubberized waterproof fire retardant membrane on steel, cementitious, modified bitumen and other substrates.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Water-based with low VOCs</li> <li>• Rapid setting</li> <li>• High elongation and tensile strength</li> <li>• Puncture resistant</li> <li>• Low permeation rates</li> <li>• Excellent chemical resistance</li> <li>• Sag resistant</li> <li>• Easily repairable</li> <li>• UL Class A Flame Spread rating</li> </ul>
<b>Uses</b>	<ul style="list-style-type: none"> <li>• Waterproofing</li> <li>• Roofing</li> <li>• Moisture/vapor barrier</li> <li>• Secondary containment</li> <li>• Retainage ponds</li> </ul>
<b>Color</b>	Black
<b>Finish</b>	Matte
<b>Primer</b>	Self-priming
<b>Dry Film Thickness (DFT)</b>	20 – 70 mils per coat
<b>Solids Content</b>	60% by weight 59% by volume
<b>Theoretical Coverage Rate</b>	914 square feet per gallon at 1 mil DFT
<b>Maximum Dry Temperature Resistance</b>	300°F (149°C)
<b>Limitations</b>	Protect from freezing

## **SUBSTRATES & SURFACE PREPARATION**

<b>All</b>	Surfaces must be clean and dry. Remove all dirt, dust, oil and all other contaminants.
<b>Previously Painted Surfaces</b>	Consult with ErgonArmor Technical Service Department.

## **MIXING & THINNING**

<b>Mixing</b>	Gentle agitation recommended.
<b>Thinning</b>	Do not thin

<b>Ratio</b>	Two component. Set ratio through proprietary spray equipment. Consult with ErgonArmor Technical Service Department.
--------------	---

## **APPLICATION GUIDELINES**

<b>Spray Application</b>	Ertech 3135 is designed for spray application using proprietary equipment that co-sprays Ertech 3135 and an accelerator that rapidly sets the sprayed film. For information on spray equipment consult with ErgonArmor Technical Service Department.
<b>Film Thickness</b>	A film thickness of up to 125 mils wet can be achieved on vertical surfaces without sagging. For applying films thicker than 125 wet mils, consult with ErgonArmor Technical Service Department.
<b>Temperature</b>	Use in temperatures of 50°F (10°C) or higher for best performance.
<b>Brush/Roller</b>	Use Ertech 3036/3037 which can be brush or roller applied for surface preparation.
<b>Trowel</b>	Use Ertech 3037 which can be trowel applied for surface preparation.
<b>Dry-To-Touch</b>	15 minutes at 77°F (25°C). Dry times are decreased with air movement over the coating.
<b>Full Cure</b>	24 – 48 hours at 77°F (25°C). Cure times are decreased with air movement over the coating.

## **CLEANUP & SAFETY**

<b>Cleanup</b>	Tools and hands should be cleaned with diesel. Spray equipment should be flushed with diesel.
<b>Safety</b>	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
<b>Ventilation</b>	Use in well ventilated areas.

## **PACKAGING, HANDLING & STORAGE**

<b>Shelf Life</b>	6 months at 75°F (24°C) when kept at recommended storage conditions and in original unopened containers.
<b>Package Sizes &amp; Shipping Weights</b>	16 gallon keg – 146 lbs (66 kg) 53 gallon drum – 491 lbs (223 kg) 275 gallon IBC tote – 2473 lbs (1121 kg)
<b>Storage Temperature</b>	50°F – 95°F (10°C – 35°C)
<b>Storage</b>	Protect from freezing. Do not store product outside. Store indoors.

### TYPICAL PHYSICAL PROPERTIES

Density ASTM D1475-13	8.5 lbs/gal
Solids by weight ASTM D5201-05a	60%
Solids by volume ASTM D5201-05a	59%
Specific gravity	1.02
Dry-to-touch, 77°F (25°C) ASTM D5895-96	15 minutes
Full cure, 77°F (25°C)	24 – 48 hours
Viscosity, 77°F (25°C) ASTM D2983-19	300 cps
Resistance to oils, greases & solvents	Poor
VOC ASTM D3960-05	0.2 lbs/gal max
Permeance 60 mils nominal ASTM E96 A method	0.11 perms
Permeance 60 mils nominal ASTM E96 B method	0.27 perms
Hydrostatic pressure resistance 60 mils nominal ASTM C 1360	40 psi
Immersion test 60 mils nominal ASTM D870-09	Pass
Tensile strength ASTM D2370-16	103 psi
Elongation ASTM D412-16	1,085%

Rev 01/2020

#### TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see [ergonarmor.com](http://ergonarmor.com).