

SELECTION & SPECIFICATION DATA

Type	Water-based Acrylic
Description	User-friendly, single-component, thin-film waterborne coating for concrete dampproofing.
Features	<ul style="list-style-type: none"> • Water-based - environmentally and user friendly • VOC content SCAQMD-compliant • Very stable - no settling or separation • Complies with EPA 40 CFR 261 for solid waste management • Resistant to 5% hydrochloric acid, 5% sulfuric acid and 5% caustic hot ash
Uses	Dampproofing for Portland cement concrete structures
Color	Black
Finish	Gloss
Dry Film Thickness (DFT)	2 – 3 mils per coat
Solids Content	25% by weight 24% by volume
Theoretical Coverage Rate	385 square feet per gallon at 1 mil DFT
Limitations	Protect from freezing Not for immersion service

SUBSTRATES & SURFACE PREPARATION

Concrete	Surfaces must be clean and dry. Remove all dirt, dust, oil and all other contaminants.
Previously Painted Surfaces	Consult with ErgonArmor Technical Service Department.

MIXING & THINNING

Mixing	Mild agitation prior to spraying
Thinning	Generally not required
Ratio	Single component

APPLICATION GUIDELINES

Spray Application	Ertech 7230 is designed for spray application using airless equipment.
Airless Spray	For best results under a wide variety of spray conditions, a 15:1 or higher ratio pump is recommended.
Tip Size	A 0.015 in orifice tip size is recommended
Hose L/D	200 ft (maximum) x 3/8 in diameter

Whip L/D	6 ft (maximum) x 1/4 in diameter
Pump Packings	PTFE/UHMWP packings in the spray pump are recommended.
Film Thickness	Non-sagging up to 10 mils WFT on vertical surfaces
Brush/Roller	Can be brush or roller applied.
Dry-To-Touch	20 minutes at 73°F (23°C) for 3 mil film thickness. Cure times are shortened with air movement over the coating. Cure time will increase with thicker films.
Full Cure	40 minutes at 73°F (23°C) for 3 mil film thickness. Cure times are shortened with air movement over the coating. Cure time will increase with thicker films.

CLEANUP & SAFETY

Cleanup	Mineral spirits or similar solvent
Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
Ventilation	Use in well ventilated areas.

PACKAGING, HANDLING & STORAGE

Shelf Life	6 months at 75°F (24°C) when kept at recommended storage conditions and in original unopened containers.
Package Sizes & Shipping Weight	53 gallon drum - 485 lbs (220 kg) 275 gallon fiber tote - 2450 lbs (1111 kg) 275 gallon IBC tote - 2445 lbs (1109 kg)
Storage Temperature	50°F – 110°F (10°C – 43°C)
Storage	Protect from freezing. Do not store outside. Store indoors.

TYPICAL PHYSICAL PROPERTIES

Density ASTM D1475-13	8.4 lbs/gal
Solids by weight ASTM D5201-05a	25%
Solids by volume ASTM D5201-05a	24%
Specific gravity	1.01
Viscosity, 77°F (25°C) ASTM D2983-19	2,000 cps
Resistance to oils, greases & solvents	Moderate
VOC ASTM D3960-05	200 g/L (1.67 lbs/gal)
Flash point ASTM D93-18	>200°F (93.3°C)

Rev 01/2020

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.