

## SELECTION & SPECIFICATION DATA

<b>Type</b>	Epoxy Polysulfide
<b>Description</b>	Novocoat EP2900 Flexible Paste is a trowel applied flexible paste designed for applications requiring high elongation in moderate chemical environments. It is a two component elastomer designed to handle moisture, mildly acidic or mildly alkaline environments. Novocoat EP2900 Flexible Paste will provide an excellent level of protection for expansion joints and cracks in concrete subject to freeze-thaw dynamics.
<b>Features</b>	<ul style="list-style-type: none"> <li>• 100% solids, no VOCs</li> <li>• Excellent impact resistance and corrosion protection</li> <li>• Outstanding elongation - 230%</li> </ul>
<b>Uses</b>	<ul style="list-style-type: none"> <li>• Concrete expansion joint sealant</li> <li>• Concrete crack filler</li> <li>• Concrete sawcut joint filler</li> <li>• Caulk around metal supports anchored to concrete</li> </ul>
<b>Color</b>	Dark gray

## SUBSTRATES & SURFACE PREPARATION

<b>All</b>	Substrate must be clean, dry and free of contaminants.
<b>Steel</b>	<p>Immersion: SSPC-SP 10/NACE 2 Near White Metal Blast with angular profile of 2.5 – 3.5 mils.</p> <p>Non-immersion: SSPC-SP 6/NACE 3 Commercial Blast with angular profile of 1.5 – 3.0 mils, SSPC-SP2 Hand Tool or SSPC-SP3 Power Tool Cleaning are suitable for mild environments.</p> <p>Self-priming on steel.</p>
<b>Concrete or Concrete Masonry Units (CMU)</b>	Concrete must be cured a minimum of 7 days at 75°F (24°C) and 50% relative humidity or equivalent. Prepare surfaces in accordance with SSPC-SP 13/ NACE 6. Required surface profile is CSP 3-5. Voids in concrete surfaces may require filling. Mortar joints should be cured a minimum of 15 days. Prime with Novocoat SC1100 Concrete Primer.

## MIXING & THINNING

<b>Ratio</b>	1A:1B by volume
<b>Mixing</b>	Mix equal parts of the resin and hardener thoroughly until a color of material is uniform and free of streaks.
<b>Thinning</b>	Do not thin.
<b>Pot Life</b>	35 minutes at 75°F (22°C)  Pot life is shorter at higher temperatures. A larger volume of mixed material will have a shorter pot life than a smaller volume.
<b>Cleanup</b>	MIBK and Butyl Acetate (50/50) or MEK

## APPLICATION GUIDANCE

<b>Trowel</b>	Apply with bulk caulk gun, trowel, putty knife or other appropriate tool. Dip in solvent to reduce sticking.
---------------	--

## CURE SCHEDULE & RECOAT WINDOW

Recoat window at 75°F (24°C)	2 – 24 hours
Tack free at 75°F (24°C)	5 hours
Light traffic at 75°F (24°C)	24 hours
Full cure at 75°F (24°C)	7 days

## SAFETY

<b>Safety</b>	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
---------------	--

<b>Ventilation</b>	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.
--------------------	---

## PACKAGING

<b>Package Sizes</b>	Dark Gray, 18.3 lbs (8.3 kg) Kit - Part A Resin - White, 10.2 lbs (4.63 kg) Pail - Part B Hardener - Black, 8.1 lbs (3.67 kg) Pail Item #: M-EP2920-2GLKT-01
----------------------	---

## STORAGE & SHELF LIFE

<b>Shelf Life</b>	12 months at 75°F (24°C) when stored under recommended conditions.
<b>Storage Conditions</b>	40°F – 110°F (4°C – 43.3°C) 0 – 100% relative humidity  Store in a dry area out of direct sunlight. Maintain product in original packaging and sealed until ready for use.

## TYPICAL PHYSICAL PROPERTIES

TEST METHOD	RESULTS
Elongation at 1/8 in thickness	>230%
Specific gravity	Resin 1:22 Hardener 0.98

Rev 06/2020

### TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see [ergonarmor.com](http://ergonarmor.com).