

CE-133 Page 1 of 2 Flexjoint[™] Joint Sealant

SELECTION & SPECIFICATION DATA

Туре	Flexibilized epoxy joint sealant
Description	Flexjoint Joint Sealant is a self-leveling, 2- component, flexibilized epoxy joint sealant for heavy traffic areas.
Uses	 Acid brick flooring compression joints Concrete control and construction joints Concrete isolation joints Concrete cracks
Features	 Corrosion resistant Supports heavy traffic loads over joints Absorbs irreversible brick growth stresses Easy to mix High bond strength
Limitations	 Not suitable for moving expansion joints Not suitable for vertical joint sealing Not for use beyond its chemical resistance or thermal capabilities. Consult ErgonArmor with specific questions.

INSTALLATION GUIDANCE

Reference Specifications	CES-130 Installation of Joint Sealants		
Installation Conditions	Flexjoint Joint Sealant is formulated for ideal handling at 70°F (21°C). Materials and substrate should be acclimated to the air temperature prior to installation, and the air temperature should be between 50°F (10°C) and 90°F (32°C) during installation and cure. Bonding surfaces must be clean, dry and neutral pH.		
Ratio	9.1 lb resin: 0.51 lb hardener.		
Mixing	minute. Slowly add	Do not mix partial units. Mix Part A resin for 1 minute. Slowly add Part B hardener to Part A resin. Mix thoroughly for 3 full minutes.	
Work Life	45-60 minutes at 70°F (21°C) Work life is shorter at higher temperatures.		
Cleanup	Mineral spirits	Mineral spirits	
<u>CURE TIME</u>			
Temperature	Tack Free	Full Cure	
70°F (21°C)	16 hours	7 days	
<u>SAFETY</u>			
Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.		
Ventilation	Provide thorough air circulation during and afte application until the material has cured when used in enclosed areas.		



PACKAGING & ESTIMATING

CE-133 Page 2 of 2 Flexjoint[™] Joint Sealant

TYPICAL PHYSICAL PROPERTIES

Color

Product Code Packaging Flexioint Pouring 19690 4 x 0.75 gal units/case Grade, Black **Flexjoint Pouring** 19691 4 x 0.75 gal units/case Grade, Gray A 3.0 gallon case consists of 4 x 9.1 lb pails of Part A resin and 4 x 0.51 lb cans of Part B hardener. 1/4 x 1/4 inch - 235 lineal feet (72 m) per unit Theoretical 1/2 x 1/2 inch - 59 lineal feet (18 m) per unit Coverage 1/2 x 1 inch - 30 lineal feet (9 m) per unit 1 x 1 inch - 15 lineal feet (4.5 m) per unit Above coverages are for 1 unit. There are 4 units in a case. Maintain products in original packaging and Storage & sealed until ready for use. Estimated shelf life of Shelf Life Flexjoint Joint Sealant components is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions. If there is any question with respect to the guality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.

Property **Typical Value** Black or gray Self leveling Consistency Density, ASTM C138 12.5 lb per gal (1,506 kg/m³) Cured hardness, Shore D 45 Tensile strength, ASTM D412 >900 psi (6.2 MPa) Elongation, ASTM D412 >50% Adhesion to concrete, ASTM C321 Exceeds strength of concrete Primer for concrete Penntrowel[™] Epoxy Primer or Novocoat[™] SC1100 Concrete Primer

Rev 07/2020

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.

Division of Ergon Asphalt & Emulsions, Inc. | P.O. Box 1639, Jackson, MS 39215-1639 | 601-933-3381 Fax | 601-933-3595 Phone | 877-98ARMOR Toll-Free | ergonarmor.com